

422 Hammerthor TB

Product Description	Standard	Product Data
Struktur – Structure – Struktur – Structure	ISO 2424	Tufted loop pile
Gauge – Gauge – Teilung – Jauge	ISO 2424	5/32"
Luvmateriale – Pile material – Faser – Couche d'usage	DIR 96/73, 96/74	100% nylon (Antron Legacy®)
Farvning – Dyeing – Färbung – Teinture	-	Piece dyed
Bagside – Backing – Rücken – Dossier	hctl	Textile Backing (TB)
Bredde – Dimensions – Dimensionen – Dimensions	ISO 3018	400 cm
Luvhøjde – Pile height – Polhöhe – Epaisseur du velours	ISO 1766	5.0 mm
Total højde – Total height – Gesamthöhe – Epaisseur totale	ISO 1765	7.0 mm
Luvvægt – Pile weight – Polgewicht – Poids de velours	ISO 8543	650 g/m2
Totalvægt – Total weight – Gesamtgewicht – Masse totale	ISO 8543	1,850 g/m2
Noppeantal – Tufts – Noppenanzahl – Nombre de boucles	ISO 1763	106,000 tufts/m2
Antismudsbehandlet – Antisoiling treatment – Antischmutzausrüstung - Antisalisure	hctl	Yes
Brugsområder – Performance areas – Anwendungsbereiche – Domaines d'usage	EN 1307	Class 33 - Heavy contract
Antistatiske egenskaber – Static control – Antistatausrüstung – Propriétés antistatiques	hctl	Permanent antistatic
Trappeegnet – Suitable for stairs – Treppeneignung – Aptitude escaliers	EN 1963	Yes
Rullehjulsegnet – Suitable for castor chairs – Stuhlrolleneignung – Apte aux sièges à roulettes	EN 985	Yes, Continuous use
Trinlydsdæmpning – Impact sound insulation – Trittschallschutz – Isolation phonique	hctl	26 dB
Lysægted – Colorfastness to light – Lichteichtheit – Solidité de lumière	ISO 105 – B02	5 (pastel shade 4)
Vandægted – Colorfastness to water – Wassereichtheit – Solidité à l'eau	ISO 105 – E01	3
Gnidægted våd/tør – Colorfastness wet/dry – Reibechtheit nass/trocken – Solidité au frottement humide/sec	ISO 105 – X12	3/4
Brand – Fire Classification – Brandverhalten – Classement feu	EN 13501 – 1 IMO	Cfl – S1 Certified
EC Standard	EN14041	Certified
Garanti mod gennemslid – Guarantee against wear – Garantie gegen Verschleiß – Garantie contre l'usure	hctl	5 years

hctl = Internal test from Hammer Carpets test laboratory. Due to ongoing development of products above declarations may change without prior notification

